

# Bjelin Woodura Planks 3.0

## Pro Matt Lacquer

Level of use domestic: **EN ISO 10874 Class Heavy Residential (Class 23)**



Level of use commercial: **EN ISO 10874 Class Heavy Commercial (Class 33)**



Woodura	Hardened Wood
Construction	Engineered wood surface with cured wood composite core and wood backing
Surface treatment	Pro Matt Lacquer

General properties	XXL
Thickness (mm)	11.3mm
Width (mm)	271mm
Length (mm)	2378mm
Wear layer thickness (mm)	0.6mm
Micro bevel	4 Way Bevel
Locking system	5G Dry
Boards per box	3
m <sup>2</sup> per box	1.94m <sup>2</sup>
m <sup>2</sup> per pallet	93m <sup>2</sup>
Weight per m <sup>2</sup> (kg)	11kg
Weight per box (kg)	21.1kg

Classification and safety properties	Standard test method	Result
Fire resistance	EN 13501	Bfl-S1 (hardly flammable)
Thermal conductivity	EN 12664	0.16 W/(m x K)
Thermal resistance	EN 12667	0.07 (m <sup>2</sup> x K)/W
Formaldehyde emission	EN 717-1	E1
Brinell hardness	EN 1534	10 HB (mv)
Impact resistance	EN 14354	EC3
Thickness swelling	EN 14354	<8%
Wear resistance	EN 14354	>6000 cycles
Slip resistance	BS 7976 part II	Dry conditions PTV62 Wet conditions PTV43
Warranty according to wrg terms	10 Year Commercial	20 Year Residential

Installation properties	
Installation method	Floating or glue down application
Installation instructions	Download from <a href="http://www.wrg.ie">www.wrg.ie</a>
Underlayment	Whiteriver 2mm Superior Green (UFH) or Whiteriver 3mm Silent Plus
Care & maintenance Instructions	Download from <a href="http://www.wrg.ie">www.wrg.ie</a>

Copyright © Välinge Innovation 2024. Weights and dimensions may have minor variations depending on external circumstances. Bjelin reserves the right to deviate from the weight and dimensions in this technical data sheet.

